

# TEST REPORT

1. No :SSR2223009

2. Client

o Name : KCC Corporation Chung Mong Ik, Chung Mong Jin

o Address : Jeonju Industrial Complex No.2, 846 Yongam-ri, Bongdong-eup, Wanju-gun, Jeon-buk, Korea

o Date of Receipt : 2012/02/23

o Date of Issued : 2012/03/14



3. Use of Report : Quality Control

4. Test Sample : SPORTHANE TOPCOAT PTA-GREEN

5. Test Results

Test Items	Unit	Sample	Test Results	Test method used
Consistency, Krieb Units	K.U	1	89	KS M 5000 : 2009
Non-volatile content	%	1	69.9	KS M ISO 3251 : 2011
Drying time(Dry-through)	h	1	4	KS M 5000 : 2009
Gross(60°)	-	1	82	KS M ISO 2813 : 2007
Fineness of grind	μm	1	30	KS M 5000 : 2009
Density	g/mL	1	1.277	KS M ISO 2811-1 : 2007

- - - End of Report - - -

Affirmation	Tested by 	Technical Manager 
Our report apply only to the standard or procedures identifice and to the sample(s) tested unless otherwise specified. The test results are not indicative of repressentative of the qualities of the lot from which the sample was taken or of apparently identical or similar products.		

**Korea Conformity Laboratories** President Jae Bi 

Address : 459-28, Gasan-dong, Geumcheon-Gu, Seoul, Korea 031-888-9463

Result Inquiry : Advanced Materials Reliability Center ☎031-429-3454